



PRO GOLD SOFTBALL MIX

1. A blend of 2mm minus screened soil and cinder fines to create a uniform material.
2. The color of the material shall be "Reddish Brown".
3. Natracil™ organic binder as distributed by Gail Materials shall have a minimum swell volume of 35 ml/gm and shall be blended with a pug mill that includes a weight belt feeder that insures the proper ratio and the uniform blending of the binder. Bucket of Belt blending are not acceptable methods.
4. For installation of new fields place Pro Gold Softball Mix to a final minimum depth of 4 inches over native soil or a sub-base that is prepared to acceptable specifications. The finale grade should be leveled and sloped according to standard infield construction specifications. Allow for +/- 1 inch for compaction
5. For installation of existing fields, properly scarify the surface of the existing material while incorporating +/- 1 inch of Pro Gold Softball Mix. Continue placement of the remainder of Pro Gold Softball Mix that is to be installed.
6. After leveling the infield skin thoroughly water the entire infield surface until the complete depth of the Pro Gold Softball Mix is moistened. After a period of +/- 4 hours compact with a minimum 2000 lb. static drum roller. If low areas are present, scarify and level low areas with additional Pro Gold Softball Mix.
7. Supplier – Gail Materials (951) 667-6106, www.gailmaterials.net

GAIL MATERIALS

10060 Dawson Canyon Road, Corona, CA 92883
(951) 667-6106 • Fax (951) 667-6102

www.gailmaterials.net